

# GRAFICAST DECO FILMS



## REFERENCE TR120 – SILK ROAD

Released on 4<sup>th</sup> July 2018

### Description

The transparent Graficast Deco film, reference TR120 – Silk Road, is a soft structured cadmium-free glossy cast PVC film with a decorative effect. The film is provided with a pressure-sensitive permanent acrylic adhesive. This adhesive is protected by a high-quality silicone paper.

### Composition

- Film : structured multi-layered cast transparent PVC film with a decorative effect, with a thickness of 135 microns
- Adhesive : transparent permanent pressure-sensitive solvent-based acrylic adhesive, with a high resistance against UV-radiation, chemical products and humidity.
- Backing paper : siliconised white kraft-paper of 120 gr/m<sup>2</sup>

### Application

The transparent Graficast Deco films were developed for indoor- and outdoor applications. The transparent Graficast Deco films enable you to create the most stunning decorations on mirrors, glass doors, shop windows, etc...

### Product advantages

- Extremely flexible – suited for all difficult applications
- Extremely decorative – suited for all creative designs

### Product specifications

Technical properties at a relative humidity of 50 ± 5 % and a temperature of 23 ± 2°C.

		Test method	Result
1.	<b>Thickness<sup>1</sup></b>		
	Thickness vinyl	Din53370	135 microns
	Thickness vinyl + glue + backing paper	Din53370	265 microns
2.	<b>Elongation at break<sup>2</sup></b>		
	In production-length direction	Din53455	> 100 %
	In cross direction	Din53455	> 100 %
3.	<b>Dimensional stability<sup>3</sup></b>	Finat 14	< 0.20 mm
4.	<b>Degree of gloss</b>		
	Minimum (measuring angle 20°)	Din67530	not measurable because of the structure of the material
5.	<b>Adhesion strength<sup>4</sup></b>		
	After 20 minutes	Finat 1	16 N/25mm
	After 24 hours	Finat 1	22 N/25mm
6.	<b>Quickstick<sup>5</sup></b>	Finat 9	16 N
7.	<b>Expected outdoor life span<sup>6</sup></b>	-	4-5 years
8.	<b>Temperature range</b>		
	At application	-	+5°C to +40°C
	At use	-	-45°C to +115°C
9.	<b>Colour back print</b>	-	red
10.	<b>Flammability</b>		
	If applied on aluminium, glass, steel = self-extinguishing		

## Storage instructions

All Graficast materials always need to be stored in their original packing and with the original protection flanges (and preferably stored vertically).

In order to avoid any loss of quality, the Graficast materials should also be stored in suitable conditions, that is at a temperature between 10 and 20°C, and a relative humidity of 50%.

Under these conditions, the Graficast Deco materials can be stored up to one year.

## Remarks

- In order to achieve an optimal result, we advise you to clean the surface with isopropanol and/or to use a low-tack application tape !
- As the colour of the film can differ slightly for each production run, we advise you not to use films with different batch numbers in one single and critical job. The number to be taken into consideration for this purpose consists of the first 5 numbers of the 7-digit batch number.
- If several strips of TR film are applied next to each other, they always have to be applied in the same direction.

## Tip

If you wish to remove the film after a while, we advise you to use a heat gun. If any glue residues stay behind on the glass surface after taking off the film, you can simply remove them by moistening them with soap-water. Leave this to soak in for a couple of minutes, and then chip it off by means of a steel scraper (also used for removing paint stains).

## Important

The information, mentioned in this product data sheet, is based upon tests that were executed by Grafityp, and that we consider to be reliable. The information always represents an average, a minimum or a maximum value, and should be considered as such. It is only given for your information, and does not give any guarantee. It is up to the end user to decide whether or not the product is suited for his particular application.

- 1)**  
The thickness of the Grafitack materials may vary slightly. The indicated value is an average value, obtained from a series of measurements.
- 2)**  
The elongation at break of the Grafitack materials may vary slightly. The indicated value is a minimum value, obtained from a series of measurements.
- 3)**  
The dimensional stability is the shrinkage of the unprinted material in mm. This value is measured by applying the film on aluminium (10x10cm), and placing it in a hot-air oven at 70°C for 48 hours (= Finat 14 Method, adjusted according to our own internally developed procedure). The indicated value is a maximum value, obtained from a series of measurements.
- 4)**  
The adhesion strength is measured on glass, and this after 20 minutes and after 24 hours. The film is removed again in an angle of 180° and at a speed of 300 mm/min. The indicated value is an average value, obtained from a series of measurements.
- 5)**  
The "Quickstick" is the direct adhesion strength, measured on glass. The indicated value is an average value, obtained from a series of measurements.
- 6)**  
The expected outdoor life span refers to outdoor use under Central European conditions and to vertical applications. Non-vertical application can reduce the life span up to 50%. The expected life span of our films is based upon professional application on a dry, degreased and suitable background. Tropical conditions, or the use near chemical emission, may have a detrimental effect on the life span. For more detailed information we also refer to our general "Grafiprint Warranty Certificate" and to our "General Terms and Conditions of Sale and Delivery".